

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 253 181 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
30.10.2002 Bulletin 2002/44

(51) Int Cl.7: **C09K 11/79**

(21) Application number: 02005391.4

(22) Date of filing: 15.03.2002

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

- Minamoto, Maki, c/o NEC Lighting, Ltd.
Tokyo (JP)
- Ito, Kazuya, c/o NEC Lighting, Ltd.
Tokyo (JP)
- Nishikage, Yosuke, c/o NEC Lighting, Ltd.
Tokyo (JP)

(30) Priority: 22.03.2001 JP 2001083384

(71) Applicant: **NEC CORPORATION**
Tokyo (JP)

(74) Representative: **VOSSIUS & PARTNER**
Siebertstrasse 4
81675 München (DE)


(72) Inventors:
• Yoshida, Hisashi, c/o NEC Lighting, Ltd.
Tokyo (JP)

(54) **Phosphors and fluorescent lamps comprising the phosphors**

(57) A phosphor represented by the formula $(1-x) \text{CaO} \cdot x \text{Eu(O)} \cdot y \text{MgO} \cdot n \text{SiO}_2$, wherein x, y and n represent number of moles, respectively. A fluorescent lamp

comprising the above phosphor. The phosphor has stronger luminous intensity and less luminous intensity reduction after a long lighting hours.

Fig. 1



Description

[0001] The present invention relates to phosphors and fluorescent lamps utilizing phosphors, more particularly, phosphors emitting blue light and fluorescent lamps utilizing blue light emitting phosphors.

[0002] A mixture of three color phosphors emitting red, green and blue lights is utilized as phosphors for a cold cathode fluorescent lamp of three-wavelength-region emitting type whose excitation source is a mercury luminescent line or for a general fluorescent lamp. It is well known that the blue light emitting phosphor is particularly important among the three phosphors because light-emitting characteristics of the blue light emitting phosphor have a great influence on a flux of light and color rendering property. As such blue light emitting phosphor, Eu-activated barium-magnesium-aluminum oxide phosphor ($\text{BaMg}_2\text{Al}_{16}\text{O}_{27}:\text{Eu}$) has been widely utilized because of its strong luminous intensity and excellent blue color rendering property.

Although Eu-activated barium-magnesium-aluminum oxide phosphor is widely utilized as a blue light emitting phosphor as described above, it is hard to say that the luminous efficiency of the blue light emitting phosphor is sufficient. When Eu-activated barium-magnesium-aluminum oxide phosphor is utilized as a phosphor of a fluorescent lamp, the luminous intensity of blue light reduces significantly after long lighting hours compared with those of red and green light, resulting in deviation of color which is one of the causes of worsening color rendering property. On the other hand, from the viewpoint of issues concerning energy consumption, disposal of waste materials and environmental pollution, a fluorescent lamp having a longer life with bright color and without deviation of color has been demanded not only from the industries but also from general consumers.

Recently various improvement of characteristics of Eu-activated barium-magnesium-aluminum oxide phosphor has been made, however, sufficient performance has not been obtained yet.

[0003] An object of the present invention is to provide a blue light emitting phosphor whose luminous intensity is stronger and luminous intensity reduction after long lighting hours is less as compared with Eu-activated barium-magnesium-aluminum oxide phosphor, when it is utilized as a phosphor of a fluorescent lamp.

Another object of this invention is to provide a fluorescent lamp utilizing a blue light emitting phosphor whose reduction in luminous intensity after long lighting hours is small.

[0004] The present invention provides a phosphor represented by the formula $(1-x)\text{CaO} \cdot x\text{Eu}(\text{O}) \cdot y\text{MgO} \cdot n\text{SiO}_2$, wherein x, y and n represent number of moles, respectively.

The present invention also provides a fluorescent lamp comprising a phosphor of the present invention.

The present invention further provides a fluorescent lamp of three-wavelength-region emitting type comprising a mixture of a red light emitting phosphor, a green light emitting phosphor and a blue light emitting phosphor, wherein said blue light emitting phosphor is the phosphor of the present invention.

BRIEF EXPLANATION OF THE DRAWING

[0005] Fig. 1 is a graph which shows comparison of luminous intensity spectra between a blue light emitting phosphor of an example of the present invention and the conventional one.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0006] The present invention provides a phosphor represented by the formula $(1-x)\text{CaO} \cdot x\text{Eu}(\text{O}) \cdot y\text{MgO} \cdot n\text{SiO}_2$, wherein x, y and n represent number of moles, respectively.

In embodiments, the phosphor as described above is particularly effective and thus preferable when x, y and n satisfy $0.001 \leq x \leq 0.5$, $0.1 \leq y \leq 2$ and $1 \leq n \leq 3$, respectively. More preferably, x, y and n satisfy $x=0.02$, $y=1.0$ and $2.0 \leq n \leq 2.4$, respectively.

A fluorescent lamp of the present invention can comprise a mercury luminescent line as an excitation source.

A fluorescent lamp of the present invention can have a cold cathode type structure or a hot cathode type structure.

Hereinafter, embodiments for carrying out the present invention will be explained with reference to a drawing.

Example 1

[0007] Firstly, in order to prepare the blue light emitting phosphor of Example 1, 69.7g of CaCO_3 , 60g of MgCO_3 , 94g of SiO_2 , 2.9g of EuF_3 were weighed as raw materials, and charged into ethanol and stirred for 24 hours. Then, the precipitates were collected, put into a crucible and calcined at 850°C in the atmosphere of hydrogen. After the calcined product was pulverized and sieved, the sieved product was further calcined at 1300°C in the atmosphere of hydrogen. After the calcination, the product was pulverized again, dried and sieved to obtain the blue light emitting phosphor of the Example 1 represented by $0.98\text{CaO} \cdot 0.02\text{Eu}(\text{O}) \cdot \text{MgO} \cdot 2.2\text{SiO}_2$.

Example 2 and 3

[0008] Furthermore, the following blue light emitting phosphors were prepared according to the same method as that in the Example 1 by changing weight ratio of the four kinds of the raw materials (CaCO_3 , MgCO_3 , SiO_2 , EuF_3):

a blue light emitting phosphor of Example 2 represented by $0.98\text{CaO} \cdot 0.02\text{Eu(O)} \cdot \text{MgO} \cdot 2.0\text{SiO}_2$;

a blue light emitting phosphor of Example 3 represented by $0.98\text{CaO} \cdot 0.02\text{Eu(O)} \cdot \text{MgO} \cdot 2.4\text{SiO}_2$.

Comparative Example

[0009] In addition to the Examples, as a comparative example, an Eu-activated barium-magnesium-aluminum oxide phosphor ($\text{BaMg}_2\text{Al}_{16}\text{O}_{27} \cdot \text{Eu}$) was prepared which has been conventionally used as a blue light emitting phosphor.

[0010] From the observation result (referring to Fig. 1) of luminous intensity spectra due to mercury luminescent line excitation at wavelength of 254nm relating to the Example 1 and the Comparative Example, it was confirmed that the luminous intensity of the Example 1 was 105 % as a basis of 100 % of that of the Comparative Example (the conventional Eu-activated barium-magnesium-aluminum oxide phosphor). The wavelength of emission peak of the conventional Eu-activated barium-magnesium-aluminum oxide phosphor is around 450 nm, while the emission peak of the Example 1 is around 448 nm shorter in wavelength, which confirmed that the color rendering property of blue color was improved.

[0011] Then, cold cathode fluorescent lamps (tube diameter ϕ 2.6, 5W) were manufactured using blue light emitting phosphors of the Example 1 to 3, respectively, according to a conventionally known methods. For the purpose of comparison, a cold cathode fluorescent lamp was also manufactured using the conventional blue light emitting phosphor (Eu-activated barium-magnesium-aluminum oxide phosphor) of the Comparative Example described above. Initial luminous intensities and those after 2000 hours of lighting were compared among the Examples and the Comparative Example (refer to Table 1). As a result of the comparison, it was confirmed that the initial luminous intensity of the Example 1 was 105%, that of the Example 2 was 103% and that of the Example 3 was 100% as a basis of 100% of the initial luminous intensity of the fluorescent lamp which utilized the conventional blue light emitting phosphor. It was confirmed that the luminous intensity after 2000 hours of lighting of the Comparative Example was 87% which means 13% reduction, while that of the Example 1 was 97%, that of the Example 2 was 94% and that of the Example 3 was 90% which means 8 to 10% reduction in the cases of the three Examples. Therefore, the superiority in sustainability of the luminous intensity of blue light after 2000 hours was also confirmed in the case of phosphors of the Examples.

Table 1

Luminous Intensity Of Blue Light Of Fluorescent Lamps		
Composition of phosphors	Lighting hour of lamp	
	0 hour	2000 hour
Example 1 $0.98\text{CaO} \cdot 0.02\text{Eu(O)} \cdot \text{MgO} \cdot 2.2\text{SiO}_2$	105%	97%
Example 2 $0.98\text{CaO} \cdot 0.02\text{Eu(O)} \cdot \text{MgO} \cdot 2.0\text{SiO}_2$	103%	94%
Example 3 $0.98\text{CaO} \cdot 0.02\text{Eu(O)} \cdot \text{MgO} \cdot 2.4\text{SiO}_2$	100%	90%
Comparative Example (conventional blue light emitting phosphor) $\text{Ba} \cdot \text{Mg}_2 \cdot \text{Al}_{16}\text{O}_{27} : \text{Eu}$	100%	87%

[0012] Furthermore, a cold cathode fluorescent lamp of three-wavelength-region emitting type (tube diameter ϕ 2.6, 5W) was manufactured according to a conventionally known method. Utilizing $(\text{Y,Eu})_2\text{O}_3$ as a red light emitting phosphor, $(\text{La,Ce,Tb}) \text{PO}_4$ as a green light emitting phosphor, and the phosphor of the Example 1 as a blue light emitting phosphor, a correlated color temperature of 7000K was obtained by mixing these three components so that the composition of the blue light emitting phosphor was 25% in the mixture. For the purpose of comparison, a fluorescent lamp of three-wavelength-region emitting type was also manufactured according to the same method as above utilizing the conventional blue light emitting phosphor (Eu-activated barium-magnesium-aluminum oxide phosphor). Initial luminous intensities were compared among the fluorescent lamps utilizing the phosphors of the Example 1 and the Comparative Example. As a result, it was confirmed that the initial luminous intensity of the fluorescent lamp relating to the Example

1 was 103% as a basis of 100% of the fluorescent lamp utilizing the conventional blue light emitting phosphor. Therefore, the luminous intensity of the fluorescent lamp of three-wavelength-region emitting type in the case of the Example 1 was confirmed to be stronger than that in the case of the Comparative Example.

The blue light emitting phosphors relating to the Example 1 to 3 described so far are those which are represented by the formula $(1-x)\text{CaO} \cdot x\text{Eu}(\text{O}) \cdot y\text{MgO} \cdot n\text{SiO}_2$, wherein x , y and n represent number of moles, respectively. From the results of the many experiments conducted by the inventors of this invention, when the number of moles x , y and n described above satisfy the ranges of $0.001 \leq x \leq 0.5$, $0.1 \leq y \leq 2$ and $1 \leq n \leq 3$, respectively, the same effects as in the case of the Examples were confirmed to be obtained.

The application to the cold cathode fluorescent lamps of the blue light emitting phosphors relating to this invention is described in the above examples, however, this invention is not necessarily limited to these examples of the cold cathode fluorescent lamps. As for fluorescent lamps, in addition to the cold cathode fluorescent lamps, there are also hot cathode fluorescent lamps and outside-electrode type lamps with discharge in rare gas (fluorescent lamps having structures providing main discharge electrodes outside of glass bulbs and emitting light by dielectric barrier discharge by charging high-frequency voltage between the main electrodes). The blue light emitting phosphors of this invention have the same effects as in the Examples on fluorescent lamps of any structures wherein films of phosphors are formed on inner surfaces of glass bulbs.


[0013] As explained above, according to this invention, a blue light emitting phosphor, which has stronger luminous intensity and, moreover, a superior sustainability in the luminous intensity after a long lighting hours when used in a lamp, compared with the conventional blue light emitting phosphors comprising Eu-activated barium-magnesium-aluminum oxide phosphors, can be obtained and a fluorescent lamp utilizing the phosphor can be provided.


While the present invention has been described with respect to specific embodiments, it is not confined to the specific details set forth, but includes various changes and modifications that may suggest themselves to those skilled in the art, all falling within the scope of the invention as defined by the following claims.

Claims

1. A phosphor represented by the formula $(1-x)\text{CaO} \cdot x\text{Eu}(\text{O}) \cdot y\text{MgO} \cdot n\text{SiO}_2$, wherein x , y and n represent number of moles, respectively.
2. A phosphor as claimed in Claim 1, wherein the number of moles x , y and n satisfy $0.001 \leq x \leq 0.5$, $0.1 \leq y \leq 2$ and $1 \leq n \leq 3$, respectively.
3. A phosphor as claimed in Claim 1, wherein the number of moles x , y and n satisfy $x=0.02$, $y=1.0$ and $2.0 \leq n \leq 2.4$, respectively.
4. A phosphor as claimed in Claim 1, wherein the number of moles x , y and n satisfy $x=0.02$, $y=1.0$ and $n=2.2$, respectively.
5. A phosphor as claimed in Claim 1, wherein the number of moles x , y and n satisfy $x=0.02$, $y=1.0$ and $n=2.0$, respectively.
6. A phosphor as claimed in Claim 1, wherein the number of moles x , y and n satisfy $x=0.02$, $y=1.0$ and $n=2.4$, respectively.
7. A fluorescent lamp comprising any one of the phosphors as claimed in Claim 1 to Claim 6.
8. A fluorescent lamp of three-wavelength-region emitting type comprising a mixture of a red light emitting phosphor, a green light emitting phosphor and a blue light emitting phosphor, wherein said blue light emitting phosphor is any one of the phosphors as claimed in Claim 1 to Claim 6.
9. A fluorescent lamp as claimed in Claim 7 or Claim 8 comprising a mercury luminescent line as an excitation source.
10. A fluorescent lamp as claimed in Claim 7 or Claim 8 having a cold cathode type structure.
11. A fluorescent lamp as claimed in Claim 7 or Claim 8 having a hot cathode type structure.

Fig. 1





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 253 181 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
07.04.2004 Bulletin 2004/15

(51) Int Cl.7: **C09K 11/79**

(43) Date of publication A2:
30.10.2002 Bulletin 2002/44

(21) Application number: 02005391.4

(22) Date of filing: 15.03.2002

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- Minamoto, Maki, c/o NEC Lighting, Ltd.
Tokyo (JP)
- Ito, Kazuya, c/o NEC Lighting, Ltd.
Tokyo (JP)
- Nishikage, Yosuke, c/o NEC Lighting, Ltd.
Tokyo (JP)

(30) Priority: 22.03.2001 JP 2001083384

(71) Applicant: **NEC CORPORATION**
Tokyo (JP)

(74) Representative: **VOSSIUS & PARTNER**
Siebertstrasse 4
81675 München (DE)


(72) Inventors:
• Yoshida, Hisashi, c/o NEC Lighting, Ltd.
Tokyo (JP)

(54) **Phosphors and fluorescent lamps comprising the phosphors**

(57) A phosphor represented by the formula $(1-x) \text{CaO} \cdot x \text{Eu(O)} \cdot y \text{MgO} \cdot n \text{SiO}_2$, wherein x, y and n represent number of moles, respectively. A fluorescent lamp

comprising the above phosphor. The phosphor has stronger luminous intensity and less luminous intensity reduction after a long lighting hours.

Fig. 1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 00 5391

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	GB 1 205 298 A (PHILIPS) 16 September 1970 (1970-09-16) * the whole document *	1,7	C09K11/79
A	PATENT ABSTRACTS OF JAPAN vol. 0133, no. 02 (C-616), 12 July 1989 (1989-07-12) & JP 1 092288 A (NICHIA CHEM IND LTD), 11 April 1989 (1989-04-11) * abstract *	1,7	
A	GB 2 171 112 A (SONY CORP) 20 August 1986 (1986-08-20) * the whole document *	1	
A	PATENT ABSTRACTS OF JAPAN vol. 0072, no. 89 (C-202), 23 December 1983 (1983-12-23) & JP 58 168683 A (MITSUBISHI DENKI KK; others: 02), 5 October 1983 (1983-10-05) * abstract *	1	
A	PATENT ABSTRACTS OF JAPAN vol. 0131, no. 79 (C-590), 26 April 1989 (1989-04-26) & JP 1 006087 A (HITACHI LTD), 10 January 1989 (1989-01-10) * abstract *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C09K H01J
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
The Hague		18 February 2004	Drouot, M-C
CATEGORY OF CITED DOCUMENTS X particularly relevant if taken alone Y particularly relevant if combined with another document of the same category A technological background O non-written disclosure P intermediate document T theory or principle underlying the invention E earlier patent document, but published on or after the filing date D document cited in the application L document cited for other reasons & member of the same patent family, corresponding document			

EPO FORM 1501/01/02 (P/C/C1)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 00 5391

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-02-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1205298	A	16-09-1970	NL 6714517 A	29-04-1969
			AT 279737 B	10-03-1970
			BE 722852 A	24-04-1969
			DE 1802060 A1	08-05-1969
			FR 1590046 A	06-04-1970
			JP 48037714 B	13-11-1973
			SE 332674 B	15-02-1971
JP 1092288	A	11-04-1989	JP 2106700 C	06-11-1996
			JP 8026309 B	13-03-1996
GB 2171112	A	20-08-1986	JP 61174291 A	05-08-1986
JP 58168683	A	05-10-1983	NONE	
JP 1006087	A	10-01-1989	NONE	

EPOFORM P415

For more details about this annex see Official Journal of the European Patent Office, No. 12/82